

Shanghai Hite Special Alloy Co., Ltd. https://www.hitealloy.com



Ni201

1. Brief introduction:

Pure nickel has good electrical conductivity, corrossion resistance, and high melting point. It evaporate in cathode temperature range, has good emissivity to the cathode, and has sufficient thermal evaporation. It also has good machinability and formability. Also it has suitable resistivity, good emissivity, and large heat transfer coefficient. Therefore, it is mostly used for corrosion resistant members, and important parts of precision instrument structure and medical equipment, such as chemical corrosion resistant equipment, filter (cloth) for producing strong alkali, welding electrode core wire for welding pig iron, lamp pin lead for bulb factory, heating rod lead wire, etc.

2. Chemical composition:

chemical composition under GB/T5235-2007 standard:

| Grade | chemical composition,% | | | | | | | | | | |
|------------|------------------------|-------|------|-------|-------|----|-------|---|------|------|--|
| Graue | Ni+Co | Cu | Si | Mn | С | Mg | S | Р | Fe | Cr | |
| N5(N02201) | ≥99 | ≤0.25 | ≤0.3 | ≤0.35 | ≤0.02 | - | ≤0.01 | - | ≤0.4 | ≤0.2 | |

chemical composition under ASTM B160 standard:

| | chemical composition,% | | | | | | | | | |
|------------|------------------------|-------|------|-------|-------|----|-------|---|------|--|
| Grade | Ni | Cu | Si | Mn | С | Mg | S | Р | Fe | |
| UNS N02201 | ≥99 | ≤0.25 | ≤0.3 | ≤0.35 | ≤0.02 | - | ≤0.01 | - | ≤0.4 | |



3. Produce standards:

| Wire/Rod/bar | ASTM B160 | ASME SB160 | | | |
|-------------------|--------------------------------|------------------------------------|--|--|--|
| strip/sheet/plate | ASTM B162 | ASME SB162 | | | |
| pipe/tube | ASTM B161/B163, ASTM B725/B730 | ASME SB161/SB163, ASME SB725/SB730 | | | |

4. Main product types:

wire,rod, bar,strip,sheet, tube.

5. Main specifications::

Ni201, N02201,N4, N6.

6. Ni201 source URL:

Shanohai Hite Special Alloy Contract https://www.hitealloy.com/product/ni201-n5.html